



Technical Data:

Weight	: 190 g/m <sup>2</sup>	±10 %	DIN 53854
Total Thickness	: 0.70 mm	±0.1 mm	
Roll Length	: 25 Meter	± 0.2 Mtr	
Roll Width	: 960 mm	± 10 mm	

Data TEXTILE GLASGEWEBE:

Net Weight	: 92 g/m <sup>2</sup>	±10 %	DIN 53854
Appreture Weight	: 28 g/m <sup>2</sup>	±10 %	DIN 53854
Chain	: 32 Threads / cm	±1 Thread	DIN 53854
Shot	: 20 Threads / cm	±1 Thread	DIN 53854
Break Stability Chain	: Approx 1000 N/5 cm		
Break Stability Shot	: Approx 375 N/5 cm		
Thickness	: 0.60 mm	±0.1 mm	
Single Width	: 910 mm	±10 mm	
Weight	: 120 g/m <sup>2</sup>	±10 %	DIN 53854

Data Copperfleece:

Surface resistivity	: 0.01 – 0.03 Ω / cm <sup>2</sup>
Temp. Range	: -30 °C to +90 °C
Thickness	: 0.18 to 0.22 mm
Weight	: 60 g/m <sup>2</sup>

Technical Measurement: Shielding Effectiveness

15 MHz	40 MHz	200 MHz
≥ 60 dB	≥ 80 dB	≥ 100 dB
Shielding Measurement accordingly to MIL STD 285		